

SECTION 09 30 13
CERAMIC PORCELAIN TILING

PART 1 - GENERAL

1.1 RELATED DOCUMENTS

- A. Drawings and general provisions of the Contract, including General and Supplementary Conditions and Division 01 Specification Sections, apply to this Section.
- B. See Section 093050 Tile Setting Accessories

1.2 SUMMARY

- A. Section Includes:
 - 1. Porcelain Tile
 - 2. Ceramic Tile
 - 3. Thresholds

1.3 DEFINITIONS

- A. General: Definitions in the ANSI A108 series of tile installation standards and in ANSI A137.1 apply to Work of this Section unless otherwise specified.
- B. Module Size: Actual tile size plus joint width indicated.
- C. Face Size: Actual tile size, excluding spacer lugs.
- D. Wet Area: Tile surfaces that are either soaked, saturated, or regularly and frequently subjected to moisture or liquids (including water), such as gang showers, tub enclosures, showers, laundries, saunas, steam rooms, swimming pools, hot tubs, and exterior areas.

1.4 PERFORMANCE REQUIREMENTS

- A. Dynamic Coefficient of Friction (DCOF): For tile installed on level interior walkways designed to bear surface traffic when wet per Section 9 of ANSI A137.1-2012 standard for ceramic tile:
 - 1. DCOF Wet Area: Minimum 0.42 per DCOF AcuTestSM

1.5 SUBMITTALS

- A. Product Data: For each type of product indicated.
 - 1. Manufacturer's printed handling and storage instructions
 - 2. Manufacturer's printed mixing instructions
 - 3. Manufacturer's printed installation instructions.
- B. Shop Drawings: Show locations of each type of tile and tile pattern. Show widths, details, and locations of expansion, contraction, control, and isolation joints in tile substrates and finished tile surfaces.
- C. Samples for Initial Selection: For each type of tile and grout indicated. Include Samples of accessories involving color selection.
 - 1. Assembled samples mounted on a rigid panel, with grouted joints, for each type and composition of tile and for each color and finish required. Make samples at least 12 inches square, but not fewer than 4 tiles. Use grout of type and in color or colors approved for completed Work.
 - 2. Grout: Submit manufacturer's full range of standard and designated color samples.
- D. Product Certificates: For each type of product, signed by product manufacturer.

- E. Material Test Reports: For each tile-setting and -grouting product.
- F. Qualification Data: For qualified Installer.

1.6 QUALITY ASSURANCE

- A. Source Limitations for Tile: Obtain tile of each type and color or finish from one source or producer.
 - 1. Obtain tile of each size, type and color or finish from same production run and of consistent quality in appearance and physical properties for each contiguous area.
- B. Source Limitations for Setting and Grouting Materials: Obtain ingredients of a uniform quality for each mortar, adhesive, and grout component from one manufacturer and each aggregate from one source or producer.
- C. Source Limitations for Other Products: Obtain each of the following products specified in this Section from a single manufacturer for each product:
 - 1. Thresholds.
 - 2. Waterproof membrane.
 - 3. Crack isolation membrane.
 - 4. Joint sealants.
 - 5. Metal edge strips.
- D. Pre-installation Conference: Conduct pre-installation conference at the site.
 - 1. Review requirements in ANSI A108.01 for substrates and for preparation by other trades.
- E. Mockups: Build mockups as indicated on Drawings or as indicated below to verify selections made under sample submittals and to demonstrate aesthetic effects and set quality standards for materials and execution.
 - 1. Build mockup of a 2x3 area of each tile to be incorporated into the Work if approved.

1.7 DELIVERY, STORAGE, AND HANDLING

- A. Deliver and store packaged materials in original containers with seals unbroken and labels intact until time of use. Comply with requirements in ANSI A137.1 for labeling tile packages.
- B. Store tile and cementitious materials on elevated platforms, under cover, and in a dry location.
- C. Store aggregates where grading and other required characteristics can be maintained and contamination can be avoided.
- D. Store liquid materials in unopened containers and protected from freezing.
- E. Handle tile that has temporary protective coating on exposed surfaces to prevent coated surfaces from contacting backs or edges of other units. If coating does contact bonding surfaces of tile, remove coating from bonding surfaces before setting tile.

1.8 PROJECT CONDITIONS

- A. Environmental Limitations: Do not install tile until construction in spaces is complete and ambient temperature and humidity conditions are maintained at the levels indicated in referenced standards and manufacturer's written instructions.

1.9 EXTRA MATERIALS

- A. Furnish extra materials that match and are from same production runs as products installed and that are packaged with protective covering for storage and identified with labels describing contents.
 - 1. Tile and Trim Units: Furnish quantity of full-size units equal to 2 percent of amount installed for each type, composition, color, pattern, and size indicated but not less than three boxes for each tile.

PART 2 - PRODUCTS

2.1 GENERAL

- A. ANSI Ceramic Tile Standard: Provide tile that complies with ANSI A137.1 for types, compositions, and other characteristics indicated.
 - 1. Provide tile complying with Standard grade requirements unless otherwise indicated.
- B. ANSI Standards for Tile Installation Materials: Provide materials complying with ANSI A108.02, ANSI standards referenced in other Part 2 articles, ANSI standards referenced by TCA installation methods specified in tile installation schedules, and other requirements specified.
- C. Factory Blending: For tile exhibiting color variations within ranges, blend tile in factory and package so tile units taken from one package show same range in colors as those taken from other packages and match approved Samples.
- D. Mounting: For factory-mounted tile, provide back- or edge-mounted tile assemblies as standard with manufacturer unless otherwise indicated.
 - 1. Where tile is indicated for installation in wet areas, do not use back- or edge-mounted tile assemblies unless tile manufacturer specifies in writing that this type of mounting is suitable for installation indicated and has a record of successful in-service performance.

2.2 MANUFACTURER

- A. Acceptable Manufacturer: Trinity Tile; 115 SW 49th Avenue; Ocala, Florida 34474
 - 1. Substitutions: In accordance with Division 1 Section "Substitution Procedures."

2.3 TILE

- A. PWT 1 / PFT 1 – Porcelain Wall and Floor Tile
 - 1) Composition: Porcelain wall and floor tile
 - 2) Module Size:
 - a) 12" x 24"
 - 3) Trim Tile: N/A
 - 4) Color: Daltile, Linden Point, Bianco (LP19)
 - 5) Water Absorption: .1%
 - 6) Coefficient of Friction:
 - a) .52
 - 7) Frost Resistance: Resistant per ASTM C1026.
 - 8) Breaking strength: greater than 401 lbf
 - 9) Chemical resistance per ASTM C-650: Class A
- B. PWT 2 – Porcelain Wall Tile

- 1) Composition: Porcelain wall tile
 - 2) Module Size:
 - a) 12" x 24"
 - 3) Trim Tile: N/A
 - 4) Color: Daltile, Linden Point, Grigio (LP21)
 - 5) Water Absorption: .1%
 - 6) Coefficient of Friction:
 - a) .52
 - 7) Frost Resistance: Resistant per ASTM C1026.
 - 8) Breaking strength: greater than 401 lbf
 - 9) Chemical resistance per ASTM C-650: Class A
- C. PWT 3 – Porcelain Wall Tile (Backsplash)
- 1) Composition: Porcelain wall tile
 - 2) Module Size:
 - a) 12" x 12" – Navy Straight Joint
 - 3) Trim Tile: Jolly – ½ x 12
 - 4) Color: Daltile, Navy K189

2.4 THRESHOLDS

- A. Provide Schluter Reno-TK or equal at tile to carpet transition.
- B. Provide Schluter Reno-U or equal at tile to concrete transition.

2.5 WATERPROOF SUBSTRATE

- A. Install tile over waterproof substrate.

2.6 GROUT MATERIALS

- A. Standard Cement Grout: ANSI A118.6.-verify with Architect
 - B. Water-Cleanable Epoxy Grout: ANSI A118.3[, with a VOC content of 65 g/L or less when calculated according to 40 CFR 59, Subpart D].- verify with architect
1. Provide product capable of withstanding continuous and intermittent exposure to temperatures of up to 140 deg F and 212 deg F, respectively, and certified by manufacturer for intended use.

2.7 ELASTOMERIC SEALANTS

- A. General: Provide sealants, primers, backer rods, and other sealant accessories that comply with the following requirements and with the applicable requirements in Division 07 Section "Joint Sealants."
 1. Colors: Provide colors of exposed sealants to match colors of grout in tile adjoining sealed joints unless otherwise indicated.
- B. Multipart, Pourable Urethane Sealant for Use T: ASTM C 920; Type M; Grade P; Class 25; Uses T, M, A, and, as applicable to joint substrates indicated, O.

2.8 MISCELLANEOUS MATERIALS

- A. Trowelable Underlayments and Patching Compounds: Latex-modified, Portland cement-based formulation provided or approved by manufacturer of tile-setting materials for

installations indicated.

- B. Metal Edge Strips: Angle or L-shape, height to match tile and setting-bed thickness, metallic or combination of metal and PVC or neoprene base, designed specifically for flooring applications.

- 1. Basis of Design: Schluter – JOLLY.

- C. Tile Cleaner: A neutral cleaner capable of removing soil and residue without harming tile and grout surfaces, specifically approved for materials and installations indicated by tile and grout manufacturers.
- D. Grout Sealer: Manufacturer's standard silicone product for sealing grout joints and that does not change color or appearance of grout.

2.9 MIXING MORTARS AND GROUT

- A. Mix mortars and grouts to comply with referenced standards and mortar and grout manufacturers' written instructions.
- B. Add materials, water, and additives in accurate proportions.
- C. Obtain and use type of mixing equipment, mixer speeds, mixing containers, mixing time, and other procedures to produce mortars and grouts of uniform quality with optimum performance characteristics for installations indicated.

PART 3 - EXECUTION

3.1 EXAMINATION

- A. Examine substrates, areas, and conditions where tile will be installed, with Installer present, for compliance with requirements for installation tolerances and other conditions affecting performance of installed tile.
 - 1. Verify that substrates for setting tile are firm, dry, clean, free of coatings that are incompatible with tile-setting materials including curing compounds and other substances that contain soap, wax, oil, or silicone; and comply with flatness tolerances required by ANSI A108.01 for installations indicated.
 - 2. Verify that concrete substrates for tile floors installed with thin-set mortar comply with surface finish requirements in ANSI A108.01 for installations indicated.
 - a) Verify that surfaces that received a steel trowel finish have been mechanically scarified.
 - b) Verify that protrusions, bumps, and ridges have been removed by sanding or grinding.
 - 3. Verify that installation of grounds, anchors, recessed frames, electrical and mechanical units of work, and similar items located in or behind tile has been completed.
 - 4. Verify that joints and cracks in tile substrates are coordinated with tile joint locations; if not coordinated, adjust joint locations in consultation with Architect.
- B. Proceed with installation only after unsatisfactory conditions have been corrected.

3.2 PREPARATION

- A. Fill cracks, holes, and depressions in concrete substrates for tile floors installed with thin-set mortar with trowelable leveling and patching compound specifically recommended by tile-setting material manufacturer.

- B. Where indicated, prepare substrates to receive waterproofing by applying a reinforced mortar bed that complies with ANSI A108.1A and is sloped 1/4 inch per foot toward drains.
- C. Blending: For tile exhibiting color variations, verify that tile has been factory blended and packaged so tile units taken from one package show same range of colors as those taken from other packages and match approved Samples. If not factory blended, either return to manufacturer or blend tiles at Project site before installing.

3.3 TILE INSTALLATION

- A. Comply with TCA's "Handbook for Ceramic Tile Installation" for TCA installation methods specified in tile installation schedules. Comply with parts of the ANSI A108 Series "Specifications for Installation of Ceramic Tile" that are referenced in TCA installation methods, specified in tile installation schedules, and apply to types of setting and grouting materials used.
 - 1. For the following installations, follow procedures in the ANSI A108 Series of tile installation standards for providing 95 percent mortar coverage:
 - a) Tile floors in wet areas.
 - b) Tile floors composed of tiles 8 by 8 inches or larger.
 - c) Tile floors composed of rib-backed tiles.
 - B. Extend tile work into recesses and under or behind equipment and fixtures to form complete covering without interruptions unless otherwise indicated. Terminate work neatly at obstructions, edges, and corners without disrupting pattern or joint alignments.
 - C. Accurately form intersections and returns. Perform cutting and drilling of tile without marring visible surfaces. Carefully grind cut edges of tile abutting trim, finish, or built-in items for straight aligned joints. Fit tile closely to electrical outlets, piping, fixtures, and other penetrations so plates, collars, or covers overlap tile.
 - D. Provide manufacturer's standard trim shapes where necessary to eliminate exposed tile edges.
 - E. Jointing Pattern: **Lay tile in stacked bond pattern. Coordinate tile pattern with Architect prior to installation.** Lay out tile work and center tile fields in both directions in each space or on each wall area. Lay out tile work to minimize the use of pieces that are less than half of a tile, or as otherwise indicated on Drawings. Provide uniform joint widths unless otherwise indicated. **Tile joints to line up precisely from floor to wall.**
 - 1. For tile mounted in sheets, make joints between tile sheets same width as joints within tile sheets so joints between sheets are not apparent in finished work.
 - 2. Where adjoining tiles on floor, base, walls, or trim are specified or indicated to be same size, align joints.
 - 3. Where tiles are specified or indicated to be whole integer multiples of adjoining tiles on floor, base, walls, or trim, align joints unless otherwise indicated.
 - F. Joint Widths:
 - 1. 1/8" typical
 - G. Expansion Joints: Provide expansion joints and other sealant-filled joints, including control, contraction, and isolation joints, where indicated. Form joints during installation of setting materials, mortar beds, and tile. Do not saw-cut joints after installing tiles.
 - 1. Where joints occur in concrete substrates, locate joints in tile surfaces directly above them.
 - 2. Prepare joints and apply sealants to comply with requirements in Division 07 Section "Joint Sealants."

- H. Thresholds: Install stone thresholds in same type of setting bed as adjacent floor unless otherwise indicated.
- I. Metal Edge Strips: Install in locations indicated or where exposed edge of tile flooring meets carpet, wood, or other flooring that finishes flush with top of tile or where there is an exposed edge.
- J. Grout Sealer: Apply grout sealer to cementitious grout joints in tile floors according to grout-sealer manufacturer's written instructions. As soon as grout sealer has penetrated grout joints, remove excess sealer and sealer from tile faces by wiping with soft cloth.

3.4 CLEANING AND PROTECTING

- A. Cleaning: On completion of placement and grouting, clean all ceramic tile surfaces so they are free of foreign matter.
 - 1. Remove Latex-Portland cement grout residue from tile as soon as possible.
 - 2. Clean grout smears and haze from tile according to tile and grout manufacturer's written instructions. Use only cleaners recommended by tile and grout manufacturers and only after determining that cleaners are safe to use by testing on samples of tile and other surfaces to be cleaned. Protect metal surfaces and plumbing fixtures from effects of cleaning. Flush surfaces with clean water before and after cleaning.
 - 3. Remove temporary protective coating by method recommended by coating manufacturer and that is acceptable to tile and grout manufacturer. Trap and remove coating to prevent drain clogging.
- B. Protect installed tile work with kraft paper or other heavy covering during construction period to prevent staining, damage, and wear. If recommended by tile manufacturer, apply coat of neutral protective cleaner to completed tile walls and floors.
- C. Prohibit foot and wheel traffic from tiled floors for at least seven days after grouting is completed.
- D. Before final inspection, remove protective coverings and rinse neutral protective cleaner from tile surfaces.

3.5 TILE INSTALLATION SCHEDULE

- A. Interior Floor Installations, Concrete Subfloor:
 - 1. Tile Installation F115: Thin-set mortar; epoxy grout.
 - a) Thin-Set Mortar: Latex-Portland cement mortar.
 - b) Grout: Water-cleanable epoxy grout.
- B. Interior Wall Installations, on Studs or Furring:
 - 1. Tile Installation : Thin-set mortar on coated glass-mat, water-resistant gypsum backer board.
 - a) Thin-Set Mortar: Latex-Portland cement mortar.
 - b) Grout: Polymer-modified sanded Polymer-modified unsanded Water-cleanable epoxy grout.

END OF SECTION

(THIS PAGE LEFT BLANK INTENTIONALLY)