# SECTION 08 14 00 INTERIOR WOOD DOORS

#### PART 1 - GENERAL

#### 1.1 SUMMARY

- A. Section Includes:
  - 1. Interior flush wood doors transparent finish.
    - a. Fire rated doors.

## 1.2 RELATED REQUIREMENTS

- A. Door Hardware including hardware location (height): Section 08 71 00, DOOR HARDWARE.
- B. Installation of Doors and Hardware: Section 08 11 13, HOLLOW METAL DOORS AND FRAMES Section 08 71 00, DOOR HARDWARE.

#### 1.3 APPLICABLE PUBLICATIONS

- A. Comply with references to extent specified in this section.
- B. American National Standards Institute/Window and Door Manufacturers
  Association (ANSI/WDMA):
  - 1. I.S. 1A-13 Architectural Wood Flush Doors.
  - 2. I.S. 6A-13 Interior Architectural Style and Rails Doors.
- C. ASTM International (ASTM):
  - 1. E90-09 Laboratory Measurements of Airborne Sound Transmission Loss of Building Partitions and Elements.
- D. National Fire Protection Association (NFPA):
  - 1. 80-16 Fire Doors and Other Opening Protectives.
  - 2. 252-12 Fire Tests of Door Assemblies.
- E. UL LLC (UL):
  - 1. 10C-09 Positive Pressure Fire Tests of Door Assemblies.
- F. Window and Door Manufacturers Association (WDMA):
  - 1. TM 7-14 Cycle-Slam Test.
  - 2. TM 8-14 Hinge Loading Test.
  - 3. TM 10-14 Screw Holding Capacity.

# 1.4 SUBMITTALS

- A. Submittal Procedures: Section 01 33 23, SHOP DRAWINGS, PRODUCT DATA, AND SAMPLES.
- B. Submittal Drawings:
  - 1. Show size, configuration, and fabrication and installation details.
  - 2. Include details of glazing.

- 3. Indicate project specific requirements not included in Manufacturer's Literature and Data submittal.
- C. Manufacturer's Literature and Data:
  - 1. Description of each product.
  - 2. Fire rated doors showing conformance with NFPA 80.

#### D. Samples:

- Corner section of flush veneered door 300 mm (12 inches) square, showing details of construction, labeled to show grade and type number and conformance to specified standard.
- 2. Veneer sample 200 mm by 275 mm (8 inch by 11 inch) showing specified wood species sanded to receive a transparent finish. Factory finish veneer sample where the prefinished option is accepted.
- E. Test Reports: Indicate products comply with specifications.
  - 1. Screw Holding Capacity Test.
  - 2. Cycle-Slam Test.
  - 3. Hinge-Loading Test.
- F. Operation and Maintenance Data:
  - 1. Care instructions for each exposed finish product.

#### 1.5 OUALITY ASSURANCE

- A. Manufacturer Oualifications:
  - 1. Regularly and presently manufactures specified products.
  - 2. Manufactures specified products with satisfactory service on five similar installations for minimum five years.

#### 1.6 DELIVERY

- A. Deliver products in manufacturer's original sealed packaging.
  - 1. Minimum 0.15 mm (6 mil) polyethylene bags or cardboard packaging to remain unbroken during delivery and storage.
- B. Mark packaging, legibly. Indicate manufacturer's name or brand, type, and manufacture date.
  - 1. Identify door opening corresponding to Door Schedule.
- C. Before installation, return or dispose of products within distorted, damaged, or opened packaging.

## 1.7 STORAGE AND HANDLING

- A. Store products indoors in dry, weathertight conditioned facility.
  - 1. Store doors according to ANSI/WDMA I.S. 1A.
- B. Protect products from damage during handling and construction operations.

#### 1.8 FIELD CONDITIONS

# A. Environment:

- 1. Product Temperature: Minimum 21 degrees C (70 degrees F) for minimum 48 hours before installation.
- 2. Work Area Ambient Temperature Range: 21 to 27 degrees C (70 to 80 degrees F) continuously, beginning 48 hours before installation.
- 3. Install products when building is permanently enclosed and when wet construction is completed, dried, and cured.
  - a. Comply with door manufacturer's instructions for relative humidity.

#### 1.9 WARRANTY

A. Construction Warranty: FAR clause 52.246-21, "Warranty of Construction."

## PART 2 - PRODUCTS

#### 2.1 PRODUCTS - GENERAL

A. Provide each product from one manufacturer.

## 2.2 FLUSH WOOD DOORS

### A. General:

- 1. ANSI/WDMA I.S. 1A, Extra Heavy Duty.
- 2. Adhesive: Type II.
- 3. Core: Structural composite lumber, except when mineral core is required for fire rating.
- 4. Thickness: 44 mm (1-3/4 inches) unless otherwise shown or specified.

#### B. Faces:

- 1. ANSI/WDMA I.S. 1A.
- 2. One species throughout project unless scheduled or otherwise shown.
- 3. Transparent Finished Faces: Premium Grade. rotary cut, red oak.
  - a. AA Grade face veneer.
  - b. Match face veneers for doors for uniform effect of color and grain at joints.
  - c. Door Edges: Same species as door face veneer, except maple is acceptable for stile face veneer on birch doors.
  - d. In existing buildings, where doors are required to have transparent finish, use wood species, grade, and assembly of face veneers to match adjacent existing doors.

- 4. Painted Finishes: Custom Grade, mill option close grained hardwood, premium or medium density overlay.
- 5. Factory sand doors for finishing.
- C. Wood For Stops, Louvers, Muntin's and Moldings For Flush Doors Required to Have Transparent Finish:
  - Solid wood of same species as face veneer, except maple is acceptable on birch doors.
  - 2. Glazing:
    - a. On non-fire-rated doors, use applied wood stops nailed tightly on room side and attached on opposite side with flathead, countersunk wood screws, spaced approximately 125 mm (5 inches) on center.

#### D. Fire-Rated Wood Doors:

- 1. Fire Resistance Rating:
  - a. B Label: 1-1/2 hours.
  - b. C Label: 3/4 hour.
- 2. Labels:
  - a. Comply with NFPA 252, UL 10C, and labeled by qualified testing and inspection agency showing fire resistance rating.
  - b. Metal labels with raised or incised markings.
- 3. Performance Criteria for Stiles of Doors Utilizing Standard Mortise Leaf Hinges:
  - a. Hinge Loading: WDMA TM 8. An average of 10 test samples for Extra Heavy-Duty doors.
  - b. Direct Screw Withdrawal: WDMA TM 10 for Extra Heavy-Duty doors. Average of 10 test samples using a steel, fully threaded #12 wood screw.
  - c. Cycle-Slam: 1,000,000 cycles with no loose hinge screws or other visible signs of failure when tested according to WDMA TM 7.
- 4. Hardware Reinforcement:
  - a. Provide fire rated doors with hardware reinforcement blocking.
  - b. Size of lock blocks as required to secure hardware specified.
  - c. Top, Bottom and Intermediate Rail Blocks: Minimum 125 mm (5 inches) by full core width.
  - d. Reinforcement blocking in compliance with labeling requirements.
  - e. Mineral material similar to core is not acceptable.
- 5. Other Core Components: Manufacturer's standard as allowed by labeling requirements.

- 6. Glazed Vision Panel Frame: Steel approved for use in labeled doors.
- 7. Astragal: Steel type for pairs of doors.
- E. Smoke Barrier Doors:
  - 1. Glazed Vision Panel Frame: Steel approved for use in labeled doors.
  - 2. Astragal: Steel type for pairs of doors, including double egress doors.

#### 2.3 STILE AND RAIL WOOD DOORS - NOT USED

#### 2.4 FABRICATION

- A. Factory machine interior wood doors to receive hardware, bevels, undercuts, cutouts, accessories and fitting for frame.
  - 1. Factory fit fire rated doors according to NFPA 80.
- B. Rout doors for hardware using templates and location heights specified in Section 08 71 00, DOOR HARDWARE.
- C. Factory fit doors to frame, bevel lock edge of doors 3 mm (1/8 inch) for each 50 mm (2 inches) of door thickness undercut where shown.
- D. Clearances between Doors and Frames and Floors:
  - 1. Fire Rated Doors: Comply with NFPA 80.
    - a. Doors with Automatic Bottom Seal: Maximum clearance 10 mm (3/8 inch) at threshold.
    - b. Other Door Bottoms: Maximum 3 mm (1/8 inch) clearance at the jambs, heads, and meeting stiles, and a 19 mm (3/4 inch) clearance at bottom, except as otherwise specified.
  - 2. Door Jambs, Heads, and Meeting Stiles: Maximum 3 mm (1/8 inch).
- E. Provide cutouts for glazed openings.
- F. Finish surfaces, including both faces, top and bottom and edges of the doors smooth to touch.
- G. Identify each door on top edge.
  - Mark with stamp, brand, or other indelible mark, giving manufacturer's name, door's trade name, construction of door, date of manufacture and quality.
  - Mark door or provide separate certification including name of inspection organization.
  - 3. Identify door manufacturing standard, including glue type.
  - 4. Identify veneer and quality certification.
  - 5. Identification of preservative treatment for stile and rail doors.

#### 2.5 FINISHES

- A. Field Finished Doors: Seal top and bottom edges of doors with two coats of catalyzed polyurethane or water-resistant sealer.
- B. Factory Transparent Finish:
  - 1. Factory finish flush wood doors.
    - a. ANSI/WDMA I.S. 1A Section F-3 Finish System Descriptions for System 5, Conversion Varnish or System 7, Catalyzed Vinyl.

#### PART 3 - EXECUTION

## 3.1 PREPARATION

- A. Examine and verify substrate suitability for product installation.
  - 1. Verify door frames are properly anchored.
  - 2. Verify door frames are plumb, square, in plane, and within tolerances for door installation.
- B. Protect existing construction and completed work from damage.
- C. Install astragal on active leaf of pair of smoke doors and one leaf of double egress smoke doors.

#### 3.2 INSTALLATION

- A. Install products according to manufacturer's instructions and approved submittal drawings.
  - 1. Install fire rated doors according to NFPA 80.
  - When manufacturer's instructions deviate from specifications, submit proposed resolution for Contracting Officer's Representative consideration.

# 3.3 PROTECTION

- A. After installation, place shipping container over door and tape in place.
  - 1. Do not apply tape to door faces and edges.
- B. Provide protective covering over exposed hardware in addition to covering door.
- C. Maintain covering in good condition until removal is directed by Contracting Officer's Representative.

- - E N D - -