

**SECTION 08 80 00**  
**GLAZING**

**PART 1 - GENERAL**

**1.1 DESCRIPTION:**

- A. This section specifies the following:
  - 1. Glass.
  - 2. Glazing materials and accessories for both factory and field glazed assemblies.

**1.2 RELATED WORK:**

- A. Factory glazed by manufacturer in following units:
  - 1. Access Control Systems: Section 28 13 11, PHYSICAL ACCESS CONTROL SYSTEMS.
  - 2. Intrusion Detection: Section 28 16 11, INTRUSION DETECTION SYSTEM.
  - 3. Wiring (120 V AC, 15A or 20A): Section 26 05 19, LOW VOLTAGE ELECTRICAL POWER AND CONDUCTORS AND CABLES.
  - 4. Junction and Switch Boxes: Section 26 05 33, RACEWAY AND BOXES FOR ELECTRICAL SYSTEMS.

**1.3 LABELS:**

- A. Temporary labels:
  - 1. Provide temporary label on each light of glass identifying manufacturer or brand and glass type, quality, and nominal thickness.
  - 2. Label in accordance with NFRC label requirements.
  - 3. Temporary labels are to remain intact until glass is approved by Contracting Officer Representative (COR).
- B. Permanent labels:
  - 1. Locate in corner for each pane.
  - 2. Label in accordance with ANSI Z97.1 and SGCC label requirements.
    - a. Tempered glass.
    - b. Laminated glass or have certificate for panes without permanent label.
  - 4. Fire rated glazing assemblies: Mark in accordance with IBC.

**1.4 PERFORMANCE REQUIREMENTS:**

- A. General: Design glazing system consistent with guidance and practices presented in the GANA Glazing Manual, GANA Laminated Glazing Manual, and GANA Sealant Manual, as applicable to project. Installed glazing is to withstand applied loads, thermal stresses, thermal movements,

building movements, permitted tolerances, and combinations of these conditions without failure, including loss or glass breakage attributable to defective manufacture, fabrication, or installation; failure of sealants or gaskets to remain watertight and airtight; deterioration of glazing materials; unsafe engagement of the framing system; deflections beyond specified limits; or other defects in construction.

- B. Glazing Unit Design: Design glass, including engineering analysis meeting requirements of authorities having jurisdiction. Thicknesses listed are minimum. Coordinate thicknesses with framing system manufacturers.
  - 1. Design glass in accordance with ASTM E1300, and for conditions beyond the scope of ASTM E1300, by a properly substantiated structural analysis.

**1.5 SUBMITTALS:**

- A. In accordance with Section 01 33 23, SHOP DRAWINGS, PRODUCT DATA, AND SAMPLES.
- B. Manufacturer's Certificates:
  - 1. Certificate stating that fire-protection and fire-resistive glazing units meet code requirements for fire-resistance-rated assembly and applicable safety glazing requirements.
- C. Manufacturer Warranty.
- D. Manufacturer's Literature and Data:
  - 1. Glass, each kind required.
  - 2. Glazing cushion.
  - 3. Sealing compound.
- E. Samples:
  - 1. Size: 305 mm by 305 mm (12 inches by 12 inches).
- F. Preconstruction Adhesion and Compatibility Test Report: Submit glazing sealant manufacturer's test report indicating glazing sealants were tested for adhesion to glass and glazing channel substrates and for compatibility with glass and other glazing materials.

**1.6 DELIVERY, STORAGE AND HANDLING:**

- A. Delivery: Schedule delivery to coincide with glazing schedules so minimum handling of crates is required. Do not open crates except as required for inspection for shipping damage.

- B. Storage: Store cases according to printed instructions on case, in areas least subject to traffic or falling objects. Keep the storage area clean and dry.
- C. Handling: Unpack cases following printed instructions on case. Stack individual windows on edge leaned slightly against upright supports with separators between each.

**1.7 PROJECT CONDITIONS:**

Field Measurements: Field measure openings before ordering tempered glass products to assure for proper fit of field measured products.

**1.8 WARRANTY:**

- A. Construction Warranty: Comply with the FAR clause 52.246-21 "Warranty of Construction".

**1.9 APPLICABLE PUBLICATIONS:**

- A. Publications listed below form a part of this specification to the extent referenced. Publications are referenced in text by basic designation only.
- B. American Architectural Manufacturers Association (AAMA):
  - 800.....Test Methods for Sealants
  - 810.1-77.....Expanded Cellular Glazing Tape
- C. American National Standards Institute (ANSI):
  - Z97.1-14.....Safety Glazing Material Used in Building - Safety Performance Specifications and Methods of Test
- D. American Society of Civil Engineers (ASCE):
  - 7-10.....Wind Load Provisions
- E. ASTM International (ASTM):
  - C542-05(R2011).....Lock-Strip Gaskets
  - C716-06.....Installing Lock-Strip Gaskets and Infill Glazing Materials
  - C794-10.....Adhesion-in-Peel of Elastomeric Joint Sealants
  - C864-05(R2011).....Dense Elastomeric Compression Seal Gaskets, Setting Blocks, and Spacers
  - C920-14a.....Elastomeric Joint Sealants
  - C964-07(R2012).....Standard Guide for Lock-Strip Gasket Glazing
  - C1036-11(R2012).....Flat Glass
  - C1048-12.....Heat-Treated Flat Glass-Kind HS, Kind FT Coated and Uncoated Glass.
  - C1172-14.....Laminated Architectural Flat Glass

- C1349-10.....Standard Specification for Architectural Flat Glass Clad Polycarbonate
- C1376-10.....Pyrolytic and Vacuum Deposition Coatings on Flat Glass
- D635-10.....Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastic in a Horizontal Position
- D4802-10.....Poly (Methyl Methacrylate) Acrylic Plastic Sheet
- E84-14.....Surface Burning Characteristics of Building Materials
- E119-14.....Standard Test Methods for Fire Test of Building Construction and Material
- E1300-12a.....Load Resistance of Glass in Buildings
- E1886-13a.....Standard Test Method for Performance of Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Missile(s) and Exposed to Cyclic Pressure Differentials
- E1996-14a.....Standard Specification for Performance of Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in Hurricanes
- E2240-06.....Test Method for Assessing the Current-Voltage Cycling Stability at 90 Degree C (194 Degree F) of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units
- E2241-06.....Test Method for Assessing the Current-Voltage Cycling Stability at Room Temperature of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units
- F1233-08.....Standard Test Method for Security Glazing Materials and Systems
- F1642-12.....Test Method for Glazing and Glazing Systems Subject to Air blast Loadings.
- E. Code of Federal Regulations (CFR):
  - 16 CFR 1201-10.....Safety Standard for Architectural Glazing Materials

- F. Glass Association of North America (GANA):
  - 2010 Edition.....GANA Glazing Manual
  - 2008 Edition.....GANA Sealant Manual
  - 2009 Edition.....GANA Laminated Glazing Reference Manual
  - 2010 Edition.....GANA Protective Glazing Reference Manual
- G. International Code Council (ICC):
  - IBC.....International Building Code
- H. Insulating Glass Certification Council (IGCC)
- I. Insulating Glass Manufacturer Alliance (IGMA):
  - TB-3001-13.....Guidelines for Sloped Glazing
  - TM-3000.....North American Glazing Guidelines for Sealed  
 Insulating Glass Units for Commercial and  
 Residential Use
- J. Intertek Testing Services - Warnock Hersey (ITS-WHI)
- K. National Fire Protection Association (NFPA):
  - 80-16.....Fire Doors and Windows
  - 252-12.....Fire Tests of Door Assemblies
  - 257-12.....Standard on Fire Test for Window and Glass  
 Block Assemblies
- L. National Fenestration Rating Council (NFRC)
- M. Safety Glazing Certification Council (SGCC) 2012:  
 Certified Products Directory (Issued Semi-Annually).
- N. Underwriters Laboratories, Inc. (UL):
  - 9-08 (R2009).....Fire Tests of Window Assemblies
  - 263-14.....Fire Tests of Building Construction and  
 Materials
  - 752-11.....Bullet-Resisting Equipment.
- O. Unified Facilities Criteria (UFC):
  - 4-010-01-03 (R2007).....DOD Minimum Antiterrorism Standards for  
 Buildings
- P. U.S. Veterans Administration:
  - Physical Security Design Manual for VA Facilities (VAPSDG); Life Safety  
 Protected
  - Physical Security Design Manual for VA Facilities (VAPSDG); Mission  
 Critical Facilities
  - Architectural Design Manual for VA Facilities (VASDM)
- Q. Environmental Protection Agency (EPA):

**PART 2 - PRODUCT**

**2.1 GLASS:**

- A. Provide minimum thickness stated and as additionally required to meet performance requirements.
  - 1. Provide a minimum of 6 mm (1/4 inch) thick glass units unless otherwise indicated.
- B. Obtain glass units from single source from single manufacturer for each glass type.
- C. Clear Glass:
  - 1. ASTM C1036, Type I, Class 1, Quality q4.

**2.2 HEAT-TREATED GLASS:**

- A. Roller Wave Limits for Heat-Treated Glass: Orient all roller wave distortion parallel to bottom surface of glazing, and provide units complying with the following limitations:
  - 1. Measurement Parallel to Line: Maximum peak to valley 0.203 mm (0.008 inch).
  - 2. Measurement Perpendicular to Line: Maximum 0.0254 mm (0.001 inch).
  - 3. Bow/Warp: Maximum 50 percent of bow and warp allowed by ASTM C1048.
- B. Clear Heat Strengthened Glass:
  - 1. ASTM C1048, Kind HS, Condition A, Type I, Class 1, Quality q3.
- C. Clear Tempered Glass:
  - 1. ASTM C1048, Kind FT, Condition A, Type I, Class 1, Quality q3.

**2.3 COATED GLASS - NOT USED**

**2.4 ELECTROCHROMIC COATED GLASS - NOT USED**

**2.5 PLASTIC GLAZING - NOT USED**

**2.6 LAMINATED GLASS - NOT USED**

**2.7 SECURITY GLAZING ASSEMBLY - NOT USED**

**2.8 INSULATING GLASS UNITS - NOT USED**

**2.9 FIRE PROTECTION AND FIRE RESISTANCE GLAZING**

- A. Fire-Protection-Rated Glazing: Glazing units tested for use in fire door assemblies or fire windows, UL, ITS-WHI or equivalent listed and labeled by testing agency in accordance with IBC, for fire-protection ratings as indicated on construction documents scheduled, based upon

positive-pressure testing per NFPA 257 or UL 9, and complying with NFPA 80.

1. Hose-Stream Test: Units must comply, except units having fire-protection rating of 20 minutes.
  2. Labeling: Permanently label fire-protection-rated glazing units in accordance with IBC.
  3. Safety Glazing: Comply with 16 CFR 1201, Category II.
  5. Fire-Protection-Rated Tempered Glass: For 20-minute fire-protection-rated door assemblies, of thickness scheduled.
- B. Fire-Resistance-Rated Glazing: Glazing units tested for use in fire wall assemblies, UL, ITS-WHI or equivalent listed and labeled by testing agency in accordance with IBC for fire-resistance ratings of wall assemblies as indicated on construction documents, based upon testing according to NFPA 252 and ASTM E119 or UL 263.
1. Labeling: Permanently label fire-resistance-rated glazing units in accordance with IBC.
  2. Safety Glazing: Comply with 16 CFR 1201, Category II.

#### **2.10 SWITCHABLE PRIVACY GLASS - NOT USED**

#### **2.11 INSULATING PLASTIC SHEETS - NOT USED**

#### **2.12 GLAZING ACCESSORIES**

- A. As required to supplement the accessories provided with the items to be glazed and to provide a complete installation. Ferrous metal accessories exposed in the finished work are to have a finish that will not corrode or stain while in service. Fire rated glazing to be installed with glazing accessories in accordance with the manufacturer's installation instructions.
- B. Setting Blocks: ASTM C864:
1. Silicone type.
  2. Channel shape; having 6 mm (1/4 inch) internal depth.
  3. Shore A hardness of 80 to 90 Durometer.
  4. Block lengths: 50 mm (2 inches) except 100 to 150 mm (4 to 6 inches) for insulating glass.
  5. Block width: Approximately 1.6 mm (1/16 inch) less than the full width of the rabbet.
  6. Block thickness: Minimum 4.8 mm (3/16 inch). Thickness sized for rabbet depth as required.
- C. Spacers: ASTM C864:
1. Channel shape having a 6 mm (1/4 inch) internal depth.

2. Flanges not less than 2.4 mm (3/32 inch) thick and web 3 mm (1/8 inch) thick.
3. Lengths: 25 to 76 mm (1 to 3 inches).
4. Shore A hardness of 40 to 50 Durometer.

D. Glazing Tapes:

1. Semi-solid polymeric based closed cell material exhibiting pressure-sensitive adhesion and withstanding exposure to sunlight, moisture, heat, cold, and aging.
2. Shape, size and degree of softness and strength suitable for use in glazing application to prevent water infiltration.
3. Complying with AAMA 800 for the following types:
  - a. AAMA 810.1, Type 1, for glazing applications in which tape acts as the primary sealant.
  - b. AAMA 810.1, Type 2, for glazing applications in which tape is used in combination with a full bead of liquid sealant.

E. Glazing Gaskets: ASTM C864:

1. Firm dense wedge shape for locking in sash.
2. Soft, closed cell with locking key for sash key.
3. Flanges may terminate above the glazing-beads or terminate flush with top of beads.

F. Glazing Sealants: ASTM C920, silicone neutral cure:

1. Type S.
2. Class 25 or 50 as recommended by manufacturer for application.
3. Grade NS.
4. Shore A hardness of 25 to 30 Durometer.

G. Neoprene, EPDM, or Vinyl Glazing Gasket: ASTM C864.

1. Channel shape; flanges may terminate above the glazing channel or flush with the top of the channel.
2. Designed for dry glazing.

H. Color:

1. Color of glazing compounds, gaskets, and sealants used for aluminum color frames to match color of the finished aluminum and be nonstaining.
2. Color of other glazing compounds, gaskets, and sealants which will be exposed in the finished work and unpainted are to be black, gray, or neutral color.

## **PART 3 - EXECUTION**

### **3.1 EXAMINATION:**

- A. Verification of Conditions:
  - 1. Examine openings for glass and glazing units; determine they are proper size; plumb; square; and level before installation is started.
  - 2. Verify that glazing openings conform with details, dimensions and tolerances indicated on manufacturer is approved shop drawings.
- B. Review of conditions which may adversely affect glass and glazing unit installation, prior to commencement of installation. Do not proceed with installation until unsatisfactory conditions have been corrected.
- C. Verify that wash down of adjacent masonry is completed prior to erection of glass and glazing units.

### **3.2 PREPARATION:**

- A. For sealant glazing, prepare glazing surfaces in accordance with GANA Sealant Manual.
- B. Determine glazing unit size and edge clearances by measuring the actual unit to receive the glazing.
- C. Shop fabricate and cut glass with smooth, straight edges of full size required by openings to provide GANA recommended edge clearances.
- D. Verify that components used are compatible.
- E. Clean and dry glazing surfaces.
- F. Prime surfaces are scheduled to receive sealants, as determined by preconstruction sealant-substrate testing.

### **3.3 INSTALLATION - GENERAL:**

- A. Install in accordance with GANA Glazing Manual, GANA Sealant Manual, IGMA TB-3001, and IGMA TM-3000 unless specified otherwise.
- B. Glaze in accordance with recommendations of glazing and framing manufacturers, and as required to meet the Performance Test Requirements specified in other applicable sections of specifications.
- C. Set glazing without bending, twisting, or forcing units.
- D. Do not allow glass to rest on or contact any framing member.
- E. Glaze doors and operable sash, in a securely fixed or closed and locked position, until sealant, glazing compound, or putty has thoroughly set.
- F. Tempered Glass: Install roller distortions in horizontal position unless otherwise directed.
- G. Fire Protective and Fire Resistance Glass:

1. Other fire protective and fire-resistant glass: Glaze in accordance with manufacturer's installation instructions and NFPA 80.

**3.4 INSTALLATION - ELECTROCHROMIC GLAZING - NOT USED**

**3.5 INSTALLATION - DRY METHOD (TAPE AND GASKET SPLINE GLAZING) - NOT USED**

**3.6 INSTALLATION - WET/DRY METHOD (PREFORMED TAPE AND SEALANT)**

- A. Cut glazing tape to length and set against permanent stops, 5 mm (3/16 inch) below sight line. Seal corners by butting tape and dabbing with butyl sealant.
- B. Apply heel bead of butyl sealant along intersection of permanent stop with frame ensuring full perimeter seal between glass and frame to complete the continuity of the air and vapor seal.
- C. Place setting blocks at 1/4 points with edge block no more than 152 mm (6 inches) from corners.
- D. Rest glazing on setting blocks and push against tape and heel bead of sealant with sufficient pressure to achieve full contact at perimeter of pane or glass unit.
- E. Install removable stops, with spacer strips inserted between glazing and applied stops, 6 mm (1/4 inch) below sight line. Place glazing tape on glazing pane or unit with tape flush with sight line.
- F. Fill gap between glazing and stop with sealant to depth equal to bite of frame on glazing, but not more than 9 mm (3/8 inch) below sight line. Sealant type is to be compatible with glazing tape.
- G. Apply cap bead of sealant along void between the stop and the glazing, to uniform line, flush with sight line. Tool or wipe sealant surface smooth.

**3.7 INSTALLATION - WET METHOD (SEALANT AND SEALANT)**

- A. Place setting blocks at 1/4 points and install glazing pane or unit.
- B. Install removable stops with glazing centered in space by inserting spacer shims on both sides at 600 mm (24 inch) intervals, 6 mm (1/4 inch) below sight line.
- C. Fill gaps between glazing and stops with sealant to depth of bite on glazing, but not more than 9 mm (3/8 inch) below sight line to ensure full contact with glazing and continue the air and vapor seal.
- D. Apply sealant to uniform line, flush with sight line. Tool or wipe sealant surface smooth.

**3.8 INSTALLATION - EXTERIOR BUTT GLAZED METHOD (SEALANT ONLY)**

**3.9 INSTALLATION - INTERIOR WET/DRY METHOD (TAPE AND SEALANT)**

- A. Cut glazing tape to length and install against permanent stops, projecting 1.6 mm (1/16 inch) above sight line.
- B. Place setting blocks at 1/4 points with edge block no more than 150 mm (6 inches) from corners.
- C. Rest glazing on setting blocks and push against tape to ensure full contact at perimeter of pane or unit.
- D. Install removable stops, spacer shims inserted between glazing and applied stops at 600 mm (24 inch) intervals, 6 mm (1/4 inch) below sight line.
- E. Fill gaps between pane and applied stop with sealant to depth equal to bite on glazing, to uniform and level line. Sealant type is to be compatible with glazing tape.
- F. Trim protruding tape edge.

**3.10 INSTALLATION - INTERIOR WET METHOD (COMPOUND AND COMPOUND)**

- A. Install glazing resting on setting blocks. Install applied stop and center pane by use of spacer shims at 600 mm (24 inch) centers, kept 6 mm (1/4 inch) below sight line.
- B. Fill gaps between glazing and stops with glazing compound until flush with sight line. Tool surface to straight line.

**3.11 INSTALLATION - REGLAZING HISTORIC FRAMING - NOT USED**

**3.12 COMMISSIONING - ELECTROCHROMIC GLAZING - NOT USED**

**3.13 REPLACEMENT AND CLEANING**

- A. Clean new glass surfaces by removing temporary labels, paint spots, and defacement after approval by COR.
- B. Replace cracked, broken, and imperfect glass, or glass which has been installed improperly.
- C. Leave glass, putty, and other setting material in clean, whole, and acceptable condition.

**3.14 PROTECTION**

**A. PROTECT FINISHED SURFACES FROM DAMAGE DURING ERECTION, AND AFTER COMPLETION OF WORK. 3.15 MONOLITHIC GLASS SCHEDULE:**

- A. Glass Type MG# 1: Clear fully tempered float glass.
  - 1. Unit Thickness: 6 mm (0.23 inch).
  - 2. Safety glazing label required.
- B. Glass Type MG# 2: Ultra-clear (low iron) fully tempered float glass.
  - 1. Unit Thickness: 6 mm (0.23 inch).

2. Safety glazing label required.

**3.16 LAMINATED GLASS SCHEDULE:**

- A. Glass Type LG# 1: Clear laminated glass with two (2) lites of fully tempered float glass.
  - 1. Minimum Thickness of Each Glass Lite: 3 mm (0.12 inch).
  - 2. Interlayer Thickness: 1.52 mm (0.060 inch).
  - 3. Safety glazing label required.
  - 4. Application: Interior glazing of units unless otherwise scheduled.

**3.17 INSULATING GLASS SCHEDULE - NOT USED**

**3.18 INSULATING LAMINATED GLASS SCHEDULE (FORCE PROTECTION AND PHYSICAL SAFETY) - NOT USED**

**3.19 ELECTROCHROMIC LAMINATED INSULATING GLASS SCHEDULE - NOT USED**

**3.20 FIRE-PROTECTIVE AND FIRE-RESISTANCE GLAZING SCHEDULE**

- A. Glass Type FR# 1: Fire-protection-rated tempered glass.
  - 1. Thickness: 6 mm (0.23 inch).
  - 2. Rating: 20 minutes.
  - 3. Application: Fire-protection-rated door assemblies with openings not over 0.65 sq. m (100 sq. in.).
- C. Glass Type FR# 2: Fire-resistance-rated laminated glass with intumescent interlayers.
  - 1. Thickness: 10mm.
  - 2. Rating: 45- minute.
  - 3. Application: Fire-protection-rated door and window assemblies.

**3.21 SECURITY GLAZING SCHEDULE: - NOT USED**

- - - E N D - - -