SECTION 08 80 00 GLAZING

PART 1 - GENERAL

1.1 DESCRIPTION:

- A. This section specifies the following:
 - 1. Glass.
 - 2. Glazing materials and accessories for both factory and field glazed assemblies.

1.2 RELATED WORK:

- A. Sustainable Design Requirements: Section 01 81 13, SUSTAINABLE CONSTRUCTION REQUIREMENTS.
- B. Factory glazed by manufacturer in following units:
 - 1. Sound resistant doors: Section 08 11 13, HOLLOW METAL DOORS AND FRAMES, and Section 08 14 00, WOOD DOORS.
 - 2. Mirrors: Section 10 28 00, TOILET, BATH, AND LAUNDRY ACCESSORIES.
 - 3. Double-Hung Windows: Section 08 52 13, ALUMINUM CLAD WOOD DOUBLE-HUNG WINDOWS.

1.3 LABELS:

- A. Temporary labels:
 - 1. Provide temporary label on each light of glass identifying manufacturer or brand and glass type, quality and nominal thickness.
 - 2. Label in accordance with NFRC label requirements.
 - 3. Temporary labels are to remain intact until glass is approved by Contracting Officer Representative (COR).

B. Permanent labels:

- 1. Locate in corner for each pane.
- 2. Label in accordance with ANSI Z97.1 and SGCC label requirements.
 - a. Tempered glass.
 - b. Laminated glass or have certificate for panes without permanent label.
 - c. Organic coated glass.
- 3. Fire rated glazing assemblies: Mark in accordance with IBC.

1.4 PERFORMANCE REQUIREMENTS:

A. General: Design glazing system consistent with guidance and practices presented in the GANA Glazing Manual, GANA Laminated Glazing Manual, and GANA Sealant Manual, as applicable to project. Installed glazing is to withstand applied loads, thermal stresses, thermal movements, building movements, permitted tolerances, and combinations of these

conditions without failure, including loss or glass breakage attributable to defective manufacture, fabrication, or installation; failure of sealants or gaskets to remain watertight and airtight; deterioration of glazing materials; unsafe engagement of the framing system; deflections beyond specified limits; or other defects in construction.

- B. Glazing Unit Design: Design glass, including engineering analysis meeting requirements of authorities having jurisdiction. Thicknesses listed are minimum. Coordinate thicknesses with framing system manufacturers.
 - 1. Design glass in accordance with ASTM E1300, and for conditions beyond the scope of ASTM E1300, by a properly substantiated structural analysis.
 - 2. Design Wind Pressures: In accordance with ASCE 7.
 - 3. Wind Design Data: In accordance with ASCE 7.
 - 4. Maximum Lateral Deflection: For glass supported on all four edges, limit center-of-glass deflection at design wind pressure to not more than the structural capacity of the glazing unit, the threshold at which frame engagement is no longer safely assured, 1/100 times the short-side length, or 19 mm (0.75 inch), whichever is less.
- C. Building Enclosure Vapor Retarder and Air Barrier:
 - 1. Utilize the inner pane of multiple pane sealed units for the continuity of the air barrier and vapor retarder seal.
 - 2. Maintain a continuous air barrier and vapor retarder throughout the glazed assembly from glass pane to heel bead of glazing sealant.

1.5 SUBMITTALS:

- A. In accordance with Section 01 33 23, SHOP DRAWINGS, PRODUCT DATA, AND SAMPLES.
- B. Sustainable Design Submittals, as described below:
 - 1. Volatile organic compounds per volume as specified in PART 2 PRODUCTS.
- C. Manufacturer's Certificates:
 - 1. Certificate stating that fire-protection and fire-resistive glazing units meet code requirements for fire-resistance-rated assembly and applicable safety glazing requirements.
 - 2. Certificate on solar heat gain coefficient when value is specified.
 - 3. Certificate on "R" value when value is specified.

- 4. Certificate test reports confirming compliance with specified bullet resistive rating.
- 5. Certificate that blast resistant glass meets the specified requirements.
- D. Manufacturer Warranty.
- E. Manufacturer's Literature and Data:
 - 1. Glass, each kind required.
 - 2. Insulating glass units.
 - 3. Transparent (one-way vision glass) mirrors.
 - 4. Elastic compound for metal sash glazing.
 - 5. Putty, for wood sash glazing.
 - 6. Glazing cushion.
 - 7. Sealing compound.
 - 8. Bullet resistive material.
 - 9. Plastic glazing material, each type required.

F. Samples:

- 1. Size: 305 mm by 305 mm (12 inches by 12 inches).
- 2. Tinted glass.
- G. Preconstruction Adhesion and Compatibility Test Report: Submit glazing sealant manufacturer's test report indicating glazing sealants were tested for adhesion to glass and glazing channel substrates and for compatibility with glass and other glazing materials.

1.6 DELIVERY, STORAGE AND HANDLING:

- A. Delivery: Schedule delivery to coincide with glazing schedules so minimum handling of crates is required. Do not open crates except as required for inspection for shipping damage.
- B. Storage: Store cases according to printed instructions on case, in areas least subject to traffic or falling objects. Keep storage area clean and dry.
- C. Handling: Unpack cases following printed instructions on case. Stack individual windows on edge leaned slightly against upright supports with separators between each.
- D. Protect laminated security glazing units against face and edge damage during entire sequence of fabrication, handling, and delivery to installation location. Provide protective covering on exposed faces of glazing plastics, and mark inside as "INTERIOR FACE" or "PROTECTED FACE":

- 1. Treat security glazing as fragile merchandise, and packaged and shipped in export wood cases with width end in upright position and blocked together in a mass. Storage and handling to comply with manufacturer's directions and as required to prevent edge damage or other damage to glazing resulting from effects of moisture, condensation, temperature changes, direct exposure to sun, other environmental conditions, and contact with chemical solvents.
- 2. Protect sealed-air-space insulating glazing units from exposure to abnormal pressure changes, as could result from substantial changes in altitude during delivery by air freight. Provide temporary breather tubes which do not nullify applicable warranties on hermetic seals.
- 3. Temporary protections: The glass front and polycarbonate back of glazing are to be temporarily protected with compatible, peelable, heat-resistant film which will be peeled for inspections and re-applied and finally removed after doors and windows are installed at destination. Since many adhesives will attack polycarbonate, the film used on exposed polycarbonate surfaces is to be approved and applied by manufacturer.
- 4. Edge protection: To cushion and protect glass clad, and polycarbonate edges from contamination or foreign matter, the four (4) edges are to be sealed the depth of glazing with continuous standard-thickness thermoplastic rubber tape. Alternatively, continuous channel shaped extrusion of thermoplastic rubber are to be used, with flanges extending into face sides of glazing.
- 5. Protect "Constant Temperature" units including every unit where glass sheet is directly laminated to or directly sealed with metal-tube type spacer bar to polycarbonate sheet, from exposures to ambient temperatures outside the range of 16 to 24 degrees C (60 to 75 degrees F), during the fabricating, handling, shipping, storing, installation, and subsequent protection of glazing.

1.7 PROJECT CONDITIONS:

Field Measurements: Field measure openings before ordering tempered glass products to assure for proper fit of field measured products.

1.8 WARRANTY:

A. Construction Warranty: Comply with the FAR clause 52.246-21 "Warranty of Construction".

- B. Manufacturer Warranty: Manufacturer shall warranty their glazing from the date of installation and final acceptance by the Government as follows. Submit manufacturer warranty.
 - 1. Bullet resistive plastic material to remain visibly clear without discoloration for 10 years.
 - 2. Insulating glass units to remain sealed for ten (10) years.
 - 3. Laminated glass units to remain laminated for five (5) years.
 - 4. Polycarbonate to remain clear and ultraviolet light stabilized for five (5) years.
 - 5. Insulating plastic to not have more than 6 percent decrease in light transmission and be ultraviolet light stabilized for ten (10) years.

1.9 APPLICABLE PUBLICATIONS:

- A. Publications listed below form a part of this specification to extent referenced. Publications are referenced in text by basic designation only.
- B. American Architectural Manufacturers Association (AAMA): 800.....Test Methods for Sealants 810.1-77.....Expanded Cellular Glazing Tape C. American National Standards Institute (ANSI): Z97.1-14.....Safety Glazing Material Used in Building - Safety Performance Specifications and Methods of Test D. American Society of Civil Engineers (ASCE): 7-10.....Wind Load Provisions E. ASTM International (ASTM): C542-05(R2011).....Lock-Strip Gaskets C716-06......Installing Lock-Strip Gaskets and Infill Glazing Materials C794-10......Adhesion-in-Peel of Elastomeric Joint Sealants C864-05(R2011)......Dense Elastomeric Compression Seal Gaskets, Setting Blocks, and Spacers C920-14a.....Elastomeric Joint Sealants C964-07(R2012)......Standard Guide for Lock-Strip Gasket Glazing C1036-11(R2012)...........Flat Glass and Uncoated Glass.

C1172-14.....Laminated Architectural Flat Glass

C1349-10	Standard Specification for Architectural Flat
	Glass Clad Polycarbonate
C1376-10	Pyrolytic and Vacuum Deposition Coatings on
	Flat Glass
D635-10	Rate of Burning and/or Extent and Time of
	Burning of Self-Supporting Plastic in a
	Horizontal Position
D4802-10	Poly (Methyl Methacrylate) Acrylic Plastic
	Sheet
E84-14	Surface Burning Characteristics of Building
	Materials
E119-14	Standard Test Methods for Fire Test of Building
	Construction and Material
E1300-12a	Load Resistance of Glass in Buildings
E1886-13a	Standard Test Method for Performance of
	Exterior Windows, Curtain Walls, Doors, and
	Impact Protective Systems Impacted by
	Missile(s) and Exposed to Cyclic Pressure
	Differentials
E1996-14a	Standard Specification for Performance of
E1996-14a	Standard Specification for Performance of Exterior Windows, Curtain Walls, Doors, and
E1996-14a	
E1996-14a	Exterior Windows, Curtain Walls, Doors, and
	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne
	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in Hurricanes
	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in HurricanesTest Methods for Assessing the Durability of
E2141-12	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in HurricanesTest Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed
E2141-12	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in HurricanesTest Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units
E2141-12	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in HurricanesTest Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass UnitsInsulating Glass Unit
E2141-12	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in Hurricanes Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Insulating Glass Unit Test Method for Assessing the Current-Voltage
E2141-12	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in Hurricanes Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Insulating Glass Unit Test Method for Assessing the Current-Voltage Cycling Stability at 90 Degree C (194 Degree F)
E2141-12 E2190-10 E2240-06	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in Hurricanes Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Insulating Glass Unit Test Method for Assessing the Current-Voltage Cycling Stability at 90 Degree C (194 Degree F) of Absorptive Electrochromic Coatings on Sealed
E2141-12 E2190-10 E2240-06	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in Hurricanes Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Insulating Glass Unit Test Method for Assessing the Current-Voltage Cycling Stability at 90 Degree C (194 Degree F) of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units
E2141-12 E2190-10 E2240-06	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in Hurricanes Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Insulating Glass Unit Orective Systems Impacted by Windborne Debris in Hurricanes Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Stability at 90 Degree C (194 Degree F) Of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Test Method for Assessing the Current-Voltage
E2141-12 E2190-10 E2240-06	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in Hurricanes Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Insulating Glass Unit Test Method for Assessing the Current-Voltage Cycling Stability at 90 Degree C (194 Degree F) of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Test Method for Assessing the Current-Voltage Cycling Stability at Room Temperature of
E2141-12 E2190-10 E2240-06	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in Hurricanes Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Insulating Glass Unit Test Method for Assessing the Current-Voltage Cycling Stability at 90 Degree C (194 Degree F) of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Test Method for Assessing the Current-Voltage Cycling Stability at Room Temperature of Absorptive Electrochromic Coatings on Sealed
E2141-12 E2190-10 E2240-06	Exterior Windows, Curtain Walls, Doors, and Impact Protective Systems Impacted by Windborne Debris in Hurricanes Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Insulating Glass Unit Test Method for Assessing the Current-Voltage Cycling Stability at 90 Degree C (194 Degree F) of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units Test Method for Assessing the Current-Voltage Cycling Stability at Room Temperature of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units

	TOOLE 10 The Marked for Margurian the Wieible Light
	E2355-10Test Method for Measuring the Visible Light
	Transmission Uniformity of an Absorptive
	Electrochromic Coating on a Glazing Surface
	F1233-08Standard Test Method for Security Glazing
	Materials and Systems
	F1642-12Test Method for Glazing and Glazing Systems
	Subject to Airblast Loadings
F.	Code of Federal Regulations (CFR):
	16 CFR 1201-10Safety Standard for Architectural Glazing
	Materials
G.	Glass Association of North America (GANA):
	2010 EditionGANA Glazing Manual
	2008 EditionGANA Sealant Manual
	2009 EditionGANA Laminated Glazing Reference Manual
	2010 EditionGANA Protective Glazing Reference Manual
Н.	International Code Council (ICC):
	IBCInternational Building Code
I.	Insulating Glass Certification Council (IGCC)
J.	Insulating Glass Manufacturer Alliance (IGMA):
	TB-3001-13Guidelines for Sloped Glazing
	TM-3000North American Glazing Guidelines for Sealed
	Insulating Glass Units for Commercial and
	Residential Use
К.	Intertek Testing Services - Warnock Hersey (ITS-WHI)
L.	National Fire Protection Association (NFPA):
	80-16Fire Doors and Windows
	252-12Fire Tests of Door Assemblies
	257-12Standard on Fire Test for Window and Glass
	Block Assemblies
Μ.	National Fenestration Rating Council (NFRC)
Ν.	Safety Glazing Certification Council (SGCC) 2012:
	Certified Products Directory (Issued Semi-Annually).
Ο.	Underwriters Laboratories, Inc. (UL):
	9-08(R2009)Fire Tests of Window Assemblies
	263-14Fire Tests of Building Construction and
	Materials
	752-11Bullet-Resisting Equipment.
P.	Unified Facilities Criteria (UFC):

4-010-01-03(R2007).....DOD Minimum Antiterrorism Standards for Buildings

Q. U.S. Veterans Administration:

Physical Security Design Manual for VA Facilities (VAPSDG); Life Safety

Physical Security Design Manual for VA Facilities (VAPSDG); Mission Critical Facilities

Architectural Design Manual for VA Facilities (VASDM)

R. Environmental Protection Agency (EPA):

40 CFR 59(2014)......National Volatile Organic Compound Emission

Standards for Consumer and Commercial Products

PART 2 - PRODUCT

2.1 GLASS:

- A. Provide minimum thickness stated and as additionally required to meet performance requirements.
 - 1. Provide minimum 6 mm (1/4 inch) thick glass units unless otherwise indicated.
- B. Obtain glass units from single source from single manufacturer for each glass type.
- C. Clear Glass:
 - 1. ASTM C1036, Type I, Class 1, Quality q3.
- D. Ultra-clear-Low-Iron Float Glass:
 - 1. ASTM C1036, Type I, Class 1, Quality q3 and with visible light transmission of not less than 90 percent.
- E. Tinted Heat reflective and low emissivity coated glass:
 - 1. ASTM C1036, Type I, Class 2, Quality q3.
- F. Patterned and Wired Flat Glass:
 - 1. ASTM C1036, Type II, Class 1, Pattern Pl, Finish F1, Quality Q5.

2.2 HEAT-TREATED GLASS:

- A. Roller Wave Limits for Heat-Treated Glass: Orient all roller wave distortion parallel to bottom surface of glazing, and provide units complying with the following limitations:
 - 1. Measurement Parallel to Line: Maximum peak to valley 0.203 mm (0.008 inch).
 - 2. Measurement Perpendicular to Line: Maximum 0.0254 mm (0.001 inch).
 - 3. Bow/Warp: Maximum 50 percent of bow and warp allowed by ASTM C1048.
- B. Clear Heat Strengthened Glass:

- 1. ASTM C1048, Kind HS, Condition A, Type I, Class 1, Quality q3.
- C. Tinted Heat Strengthened Glass:
 - 1. ASTM C1048, Kind HS, Condition A, Type I, Class 2, Quality q3.
- D. Clear Tempered Glass:
 - 1. ASTM C1048, Kind FT, Condition A, Type I, Class 1, Quality q3.
- E. Tinted Tempered Glass.
 - 1. ASTM C1048, Kind FT, Condition A, Type I, Class 2, Quality q3.
- F. Tempered Patterned Glass:
 - 1. ASTM C1048, Kind FT, Type II, Class 1, Form 3, finish, pattern and quality as indicated in construction documents.

2.3 COATED GLASS:

- A. Silicone Coated Spandrel Glass:
 - 1. ASTM C1048, Kind HS or FT, Condition B, Type I, Quality q3 with silicone coating applied over glass surface.
 - 2. Pattern as scheduled.
- 2.4 ELECTROCHROMIC COATED GLASS: NOT USED
- 2.5 PLASTIC GLAZING: NOT USED

2.6 LAMINATED GLASS:

- A. Laminated Glass: ASTM C1172. Two or more lites of glass bonded with polyvinyl butyral, ionomeric polymer, or cast-in-place and cured-transparent-resin interlayer complying with interlayer manufacturer's written instructions.
- B. Interlayer: Use min. 0.75 mm (0.030 inch) thick interlayer for vertical glazing unless otherwise indicated in construction documents.
- C. Interlayer: Use 1.5 mm (0.060 inch) thick interlayer for:
 - 1. Horizontal or sloped glazing.
 - 2. Acoustical glazing.
 - 3. Assemblies requiring heat strengthened or fully tempered glass.
- D. Interlayer: Use 2.28 mm (0.090 inch) thick interlayer where required to meet performance requirements.
- E. Interlayer Color: Clear, unless otherwise indicated in construction documents.

2.7 SECURITY GLAZING ASSEMBLY: - NOT USED

2.8 INSULATING GLASS UNITS:

A. Provide factory fabricated, hermetically sealed glass unit consisting of two panes of glass separated by a dehydrated air space and comply with ASTM E2190.

B. Assemble units using glass types specified in Insulating Glass Schedule.

2.9 FIRE PROTECTION AND FIRE RESISTANCE GLAZING:

- A. Fire-Protection-Rated Glazing: Glazing units tested for use in fire door assemblies or fire windows, UL, ITS-WHI or equivalent listed and labeled by testing agency in accordance with IBC, for fire-protection ratings as indicated on construction documents, based upon positive-pressure testing per NFPA 257 or UL 9, and complying with NFPA 80.
 - 1. Hose-Stream Test: Units must comply, except units having fireprotection rating of 20 minutes.
 - 2. Labeling: Permanently label fire-protection-rated glazing units in accordance with IBC.
 - 3. Safety Glazing: Comply with 16 CFR 1201, Category II.
 - 4. Fire-Protection-Rated Tempered Glass: For 20-minute fire-protection-rated door assemblies, of thickness scheduled.
 - 5. Fire-Protection-Rated Laminated Ceramic Glazing: Units made from two lites of clear, ceramic glass, 8 mm (5/16 inch) total thickness, for rating scheduled.
 - 6. Fire-Protection-Rated Laminated Glass with Intumescent Interlayers: Units made from multiple lites of uncoated, ultra-clear (low-iron) float glass, in intumescent interlayers, of thickness and rating scheduled.
- B. Fire-Resistance-Rated Glazing: Glazing units tested for use in fire wall assemblies, UL, ITS-WHI or equivalent listed and labeled by testing agency in accordance with IBC for fire-resistance ratings of wall assemblies as indicated on construction documents, based upon testing according to NFPA 252 and ASTM E119 or UL 263.
 - 1. Labeling: Permanently label fire-resistance-rated glazing units in accordance with IBC.
 - 2. Safety Glazing: Comply with 16 CFR 1201, Category II.
 - 3. Fire-Resistance-Rated Laminated Glass with Intumescent Interlayers:
 Units made from multiple lites of uncoated, ultra-clear low-iron
 float glass, in intumescent interlayers, of thickness and rating
 scheduled.
 - 4. Fire-Resistance-Rated Double Glazing Units with Gel Fill: Units made from two lites of uncoated, fully tempered, ultra-clear (low-iron) float glass, with perimeter metal spacer and edge seal forming

cavity filled with clear, fully transparent, heat-absorbing gel, of thickness and fire-protection rating scheduled.

2.10 SWITCHABLE PRIVACY GLASS: - NOT USED

2.11 INSULATING PLASTIC SHEETS: - NOT USED

2.12 GLAZING ACCESSORIES:

- A. As required to supplement the accessories provided with the items to be glazed and to provide a complete installation. Ferrous metal accessories exposed in the finished work are to have a finish that will not corrode or stain while in service. Fire rated glazing to be installed with glazing accessories in accordance with the manufacturer's installation instructions.
- B. Setting Blocks: ASTM C864:
 - 1. Silicone type.
 - 2. Channel shape; having 6 mm (1/4 inch) internal depth.
 - 3. Shore A hardness of 80 to 90 Durometer.
 - 4. Block lengths: 50 mm (2 inches) except 100 to 150 mm (4 to 6 inches) for insulating glass.
 - 5. Block width: Approximately 1.6 mm (1/16 inch) less than the full width of the rabbet.
 - 6. Block thickness: Minimum 4.8 mm (3/16 inch). Thickness sized for rabbet depth as required.

C. Spacers: ASTM C864:

- 1. Channel shape having a 6 mm (1/4 inch) internal depth.
- 2. Flanges not less 2.4 mm (3/32 inch) thick and web 3 mm (1/8 inch) thick.
- 3. Lengths: 25 to 76 mm (1 to 3 inches).
- 4. Shore A hardness of 40 to 50 Durometer.

D. Glazing Tapes:

- Semi-solid polymeric based closed cell material exhibiting pressure-sensitive adhesion and withstanding exposure to sunlight, moisture, heat, cold, and aging.
- 2. Shape, size and degree of softness and strength suitable for use in glazing application to prevent water infiltration.
- 3. Complying with AAMA 800 for the following types:
 - a. AAMA 810.1, Type 1, for glazing applications in which tape acts as the primary sealant.
 - b. AAMA 810.1, Type 2, for glazing applications in which tape is used in combination with a full bead of liquid sealant.

- E. Spring Steel Spacer: Galvanized steel wire or strip designed to position glazing in channel or rabbeted sash with stops.
- F. Glazing Clips: Galvanized steel spring wire designed to hold glass in position in rabbeted sash without stops.
- G. Glazing Points (Sprigs): Pure zinc stock, thin, flat, triangular or diamond shaped pieces, 6 mm (1/4 inch) minimum size.
- H. Glazing Gaskets: ASTM C864:
 - 1. Firm dense wedge shape for locking in sash.
 - 2. Soft, closed cell with locking key for sash key.
 - 3. Flanges may terminate above the glazing-beads or terminate flush with top of beads.
- I. Lock-Strip Glazing Gaskets: ASTM C542, shape, size, and mounting as indicated.
- J. Glazing Sealants: ASTM C920, silicone neutral cure:
 - 1. Type S.
 - 2. Class 25 or 50 as recommended by manufacturer for application.
 - 3. Grade NS.
 - 4. Shore A hardness of 25 to 30 Durometer.
 - 5. VOC Content: For sealants used inside the weatherproofing system, not more than 250 g/L or less when calculating according to 40 CFR 59, (EPA Method 24).

K. Color:

- Color of glazing compounds, gaskets, and sealants used for aluminum color frames to match color of the finished aluminum and be nonstaining.
- Color of other glazing compounds, gaskets, and sealants which will be exposed in the finished work and unpainted are to be black, gray, or neutral color.
- L. Smoke Removal Unit Targets: Adhesive targets affixed to glass to identify glass units intended for removal for smoke control. Comply with requirements of local Fire Department.

PART 3 - EXECUTION

3.1 EXAMINATION:

- A. Verification of Conditions:
 - 1. Examine openings for glass and glazing units; determine they are proper size; plumb; square; and level before installation is started.

- 2. Verify that glazing openings conform with details, dimensions and tolerances indicated on manufacturer is approved shop drawings.
- B. Review for conditions which may adversely affect glass and glazing unit installation, prior to commencement of installation. Do not proceed with installation until unsatisfactory conditions have been corrected.
- C. Verify that wash down of adjacent masonry is completed prior to erection of glass and glazing units.

3.2 PREPARATION:

- A. For sealant glazing, prepare glazing surfaces in accordance with GANA Sealant Manual.
- B. Determine glazing unit size and edge clearances by measuring the actual unit to receive the glazing.
- C. Shop fabricate and cut glass with smooth, straight edges of full size required by openings to provide GANA recommended edge clearances.
- D. Verify that components used are compatible.
- E. Clean and dry glazing surfaces.
- F. Prime surfaces scheduled to receive sealants, as determined by preconstruction sealant-substrate testing.

3.3 INSTALLATION - GENERAL:

- A. Install in accordance with GANA Glazing Manual, GANA Sealant Manual, IGMA TB-3001, and IGMA TM-3000 unless specified otherwise.
- B. Glaze in accordance with recommendations of glazing and framing manufacturers, and as required to meet the Performance Test Requirements specified in other applicable sections of specifications.
- C. Set glazing without bending, twisting, or forcing of units.
- D. Do not allow glass to rest on or contact any framing member.
- E. Glaze doors and operable sash, in a securely fixed or closed and locked position, until sealant, glazing compound, or putty has thoroughly set.
- F. Patterned Glass:
 - 1. Install units with one patterned surface with smooth surface on the weather side.
 - 2. Install units in interior partitions with pattern in same direction in all openings.
- G. Tempered Glass: Install with roller distortions in horizontal position unless otherwise directed.
- H. Transparent (One-Way Vision Glass) Mirror: Use continuous channel glazing gasket.
- I. Plastic:

- 1. Use dry glazing method.
- 2. Use only neoprene or EPDM gaskets.

J. Laminated Glass:

- 1. Tape edges to seal interlayer and protect from glazing sealants.
- 2. Do not use putty or glazing compounds.

K. Insulating Glass Units:

- 1. Glaze in compliance with glass manufacturer's written instructions.
- 2. When glazing gaskets are used, they are to be of sufficient size and depth to cover glass seal or metal channel frame completely.
- 3. Do not use putty or glazing compounds.
- 4. Do not grind, nip, cut, or otherwise alter edges and corners of fused glass units after shipping from factory.
- 5. Install with tape or gunnable sealant in wood sash.
- L. Fire Protective and Fire Resistance Glass:
 - 1. Wire Glass: Glaze in accordance with NFPA 80.
 - 2. Other fire protective and fire resistant glass: Glaze in accordance with manufacturer's installation instructions and NFPA 80.
- 3.4 INSTALLATION ELECTROCHROMIC GLAZING: NOT USED
- 3.5 INSTALLATION DRY METHOD (TAPE AND GASKET SPLINE GLAZING): NOT USED
- 3.6 INSTALLATION WET/DRY METHOD (PREFORMED TAPE AND SEALANT): NOT USED
- 3.7 INSTALLATION WET METHOD (SEALANT AND SEALANT): NOT USED
- 3.8 INSTALLATION EXTERIOR BUTT GLAZED METHOD (SEALANT ONLY): NOT USED
- 3.9 INSTALLATION INTERIOR WET/DRY METHOD (TAPE AND SEALANT): NOT USED
- 3.10 INSTALLATION INTERIOR WET METHOD (COMPOUND AND COMPOUND): NOT USED
- 3.11 INSTALLATION REGLAZING HISTORIC FRAMING: NOT USED
- 3.12 COMMISSIONING ELECTROCHROMIC GLAZING: NOT USED

3.13 REPLACEMENT AND CLEANING:

- A. Clean new glass surfaces removing temporary labels, paint spots, and defacement after approval by COR.
- B. Replace cracked, broken, and imperfect glass, or glass which has been installed improperly.
- C. Leave glass, putty, and other setting material in clean, whole, and acceptable condition.

3.14 PROTECTION:

A. Protect finished surfaces from damage during erection, and after completion of work. Strippable plastic coatings on colored anodized finish are not acceptable.

3.15 MONOLITHIC GLASS SCHEDULE:

Glass Type MG#1: Clear fully tempered float glass.

- 1. Unit Thickness: 6 mm (0.23 inch).
- 2. Safety glazing label required.

3.16 LAMINATED GLASS SCHEDULE:

- A. Glass Type LG#1: Clear laminated glass with two (2) lites of fully tempered float glass.
 - 1. Minimum Thickness of Each Glass Lite: 3 mm (0.12 inch).
 - 2. Interlayer Thickness: 1.52 mm (0.060 inch).
 - 3. Safety glazing label required.
 - 4. Application: Interior glazing of units unless otherwise scheduled.

3.17 INSULATING GLASS SCHEDULE:

- A. Glass Type IG# 1: Low-E-coated, clear dual insulating glass.
 - 1. Overall Unit Thickness: 25 mm (1 inch).
 - 2. Minimum Thickness of Each Glass Lite: 6 mm (0.23 inch).
 - 3. Outdoor Lite: Fully tempered float glass.
 - 4. Interspace Content: Argon.
 - 5. Indoor Lite: Fully tempered, laminated float glass.
 - 6. Low-E Coating: Sputtered on second surface.
 - 7. Visible Light Transmittance: 71 percent minimum.
 - 8. Solar Heat Gain Coefficient: .39 maximum.
 - 9. Safety glazing label required.
 - 10. U-factor: 0.24 (R4.16)11. Energy star compliant
- B. Glass Type IG# 2: Ceramic-coated, insulating spandrel glass.
 - 1. Match adjacent vision unit profile, glass thickness, tint, low-E coating, and performance.
 - 2. Overall Unit Thickness: 25 mm (1 inch)
 - 3. Minimum Thickness of Each Glass Lite: 6 mm (0.23 inch).
 - 4. Outdoor Lite: Fully tempered float glass.
 - 5. Interspace Content: Argon.
 - 6. Indoor Lite: Fully tempered, laminated float glass.
 - a. Opaque Coating Location: Fourth surface.
 - b. Coating Color: As selected by Architect from manufacturer's full range.

3.18 INSULATING LAMINATED GLASS SCHEDULE (FORCE PROTECTION AND PHYSICAL SAFETY): - NOT USED

3.19 ELECTROCHROMIC LAMINATED INSULATING GLASS SCHEDULE: - NOT USED

3.20 FIRE-PROTECTIVE AND FIRE-RESISTANCE GLAZING SCHEDULE:

- A. Glass Type FR#1: Fire-protection-rated tempered glass.
 - 1. Thickness: 6 mm (0.23 inch).
 - 2. Rating: 20 minutes.
 - 3. Application: Fire-protection-rated door assemblies with openings not over 0.65 sq. m (100 sq. in.).
- B. Glass Type FR#2: Fire-protection-rated laminated ceramic glazing.
 - 1. Thickness: 6 mm (0.23 inch)..
 - 2. Rating: 45-minute.
 - 3. Application: Fire-protection-rated door and window assemblies.
- C. Glass Type FR# 3: Fire-resistance rated, ceramic-coated, insulating spandrel glass.
 - 1. Match adjacent vision unit profile, glass thickness, tint, low-E coating, and performance.
 - 2. Rating: 60-minute.
 - 3. Overall Unit Thickness: 25 mm (1 inch) .
 - 4. Minimum Thickness of Each Glass Lite: 6 mm (0.23 inch).
 - 5. Outdoor Lite: Fully tempered float glass.
 - 6. Interspace Content: Argon.
 - 7. Indoor Lite: Fully tempered, laminated float glass.
 - a. Opaque Coating Location: Fourth surface.
 - b. Coating Color: As selected by Architect from manufacturer's full range.
 - 8. Application: Fire-protection-rated wall assemblies

3.21 SECURITY GLAZING SCHEDULE: - NOT USED

- - - E N D - - -